

**CARTULINA PARA NAIPES**

	Ref. STD	Unit of meas.	TECHNICAL SPECIFICATIONS			
Substance	ISO 536	g/m2	270	300	350	
Caliper	ISO 534	µm	270	300	360	
Bulk	ISO 534	cm3/g	1,00	1,00	1,03	
Smoothness Bekk	ISO 5627	s	230	230	170	
Gloss Gardner	ISO 8254-1	%	37	37	37	
Brightness ISO	ISO 2470 (D65)	%	91	91	91	
Opacity ISO	ISO 2471	%	100	100	100	
Stiffness L&W 15 degrees MD	ISO 2493	mN	140	190	320	
Stiffness L&W 15 degrees CD	ISO 2493	mN	70	90	140	
Scott Bond		J/m <sup>2</sup>	600 min	600 min	600 min	

Tolerances	Ref. STD	Unit of meas.	RANGE			
Substance	ISO 536	g/m2	259/281	288/312	336/364	
Caliper	ISO 534	µm	257/283	285/315	342/378	
Bulk	ISO 534	cm3/g	-	-	-	
Smoothness Bekk	ISO 5627	s	161/299	161/299	119/221	
Gloss Gardner	ISO 8254-1	%	33/41	33/41	33/41	
Brightness ISO	ISO 2470 (D65)	%	89/93	89/93	89/93	
Opacity ISO	ISO 2471	%	98/102	98/102	98/102	
Stiffness L&W 15 degrees MD	ISO 2493	mN	120/160	161/219	272/368	
Stiffness L&W 15 degrees CD	ISO 2493	mN	60/80	77/103	119/161	
Scott Bond		J/m <sup>2</sup>	600 min	600 min	600 min	

**Notes:**

Finishing **Satin**  
 Printing method **Sheet-fed offset**  
 Applications

Values referred to each quality are to be considered as reference data and could change without notice. Each value is subject to trade tolerances.

Datos facilitados por nuestro proveedor nº 1110